

# 488

## X-Coat™ Nano

Date: \_\_\_\_\_

Batch Number: \_\_\_\_\_

Yield: **92 Gallons (348 Liters)**

Essential Batch Number: \_\_\_\_\_

- 
1. Make sure blending tanks and equipment are clean.
  2. Pump 37 gallons (140 liters) of water into mixing tank.
  3. While agitating, slowly add 55 gallons (208 liters) of SUPERBASE 488.
  4. Continue agitating for (5) minutes. Batch complete.
  5. Package in clean plastic drums and containers.
  6. Product should stand for 24 hours before applying to floor.

*Note: One drum of 488 makes 92 gallons of 88.*

---

SDS and label copy for finished product may be obtained from  
Essential Industries at (800)-551-9679 or (262) 538-1122.