

# 282

## Acrylic Undercoater-Sealer (17% Solids)

Date: \_\_\_\_\_

Batch Number: \_\_\_\_\_

Yield: **123 Gallons (465 Liters)**

Essential Batch Number: \_\_\_\_\_

1. Make sure blending tanks and equipment are clean.
2. Pump 68 gallons (257 liters) of water into mixing tank.
3. While agitating, slowly add 55 gallons (208 liters) of SUPERBASE 282.
4. Agitate for (5) minutes. Batch complete.
5. Package in clean plastic drums and containers.
6. Product should stand for 24 hours before applying to floor.

*Note: One drum of 282 makes 123 gallons of 272.*

SDS and label copy for finished product may be obtained from  
Essential Industries at (800)-551-9679 or (262) 538-1122.