

# Superbase® Blend Sheet

## 474

**Eccothane  
(18% Solids)**

Date: \_\_\_\_\_

Batch Number: \_\_\_\_\_

Yield: **110 Gallons (416 Liters)**

Essential Batch Number: \_\_\_\_\_

- 
1. Make sure blending tanks and equipment are clean.
  2. Pump 55 gallons (208 liters) of water into mixing tank.
  3. While agitating, slowly add 55 gallons (208 liters) of SUPERBASE 474.
  4. Continue agitating for (5) minutes for thorough blending. Batch complete.
  5. Package in clean plastic drums and containers.
  6. Product should stand for 24 hours before applying to floor.

*Note: One drum of 474 makes 110 gallons of 274.*

---

SDS and label copy for finished product may be obtained from  
Essential Industries at (800)-551-9679 or (262) 538-1122.