

Superbase® Blend Sheet

473

**High Gloss Floor Finish
(19% solids finish)**

Date: _____

Batch Number: _____

Yield: **104 Gallons (393 Liters)**

Essential Batch Number: _____

-
1. Make sure blending tanks and equipment are clean.
 2. Pump 49 gallons (185 liters) of water into tank.
 3. While agitating, add 55 gallons (208 liters) of SUPERBASE 473.
 4. Continue agitating for (5) minutes for thorough blending.
Batch complete.
 5. Package in clean plastic drums and containers.
 6. Product should stand for 24 hours before applying to floor.

Note: One drum of 473 makes 104 gallons of High Gloss Floor Finish at 19% solids.

SDS and label copy for finished product may be obtained from Essential Industries at (800) 551-9679 or (262) 538-1122.

CONFIDENTIAL

F0118